



Rapollo Resins Stone Impregnation System

The system is a result of an intensive development with the manufacturers and users of the most advanced technology at the market today.

The systems are designed to give optimal performance: adhesion, penetration with a water-clear and high gloss surface.

| Basis: A-Pox 1200 | Vacuuminfusion / Autoclave impregnation | Block reinforcement | Slabfilling – fast polishing |
|-----------------------------|---|--|--------------------------------------|
| System | A-Pox 1200/B-Cure 33-SO *) | A-Pox 1200/B-Cure 25 Medium | A-Pox 1200/B-Cure 25 Fast |
| Mix-ratio | 100:33 | 100:25 | 100:25 |
| Viscosity mixed | 250 mPas | 300 mPas | 300 mPas |
| Pot-life 23°C-200g. | 300 min | 30 min | 25-35 min |
| Min.cure temp °C | 12 | 12 | 15 |
| Thin film set-time | 20 t | 10 t | 6 t |
| Elongation to break % | 6-8 | 4-6 | 3-5 |
| Curing in damp conditions | +++ | +++ | +++ |
| Colour | Clear | Clear | Clear |

*) Cure 70 degr.C – 8h.



Skomagervej 5A, DK – 7100 Vejle, Denmark

Phone + 45 23 48 56 79

www.rapollo.dk

Mail: info@rapollo.dk